

Instructions for Lithurin® Seal indoors

1. Apply with a low-pressure sprayer or LC applicator.
2. Lithurin® SEAL must remain wet on the surface for at least 15 minutes before it is allowed to dry.
3. Mop off the surface with a fine mop.
4. Remove excess material while it is still fluid.
5. Be sure to include all excess material that the floor doesn't absorb.
6. To ensure that the concrete surface receives the right amount of material, the instructions above must be followed carefully.
7. Under certain conditions, e.g. low temperatures, strong wind etc., the absorption time is longer and at higher temperatures the absorption time is shorter

Consumption:

- Machine trowelled surface: approx. 0.15 litres/m².
- Non-machine trowelled surface: approx. 0.2-0.4 litres/m².



ab lindec® endeavours to provide correct information about technical properties and handling of its products. However, while ab lindec® has no control over the way in which the products are mixed and laid, or the conditions under which they set, ab lindec® can in no way be held responsible. ab lindec® is only responsible for the quality of the products at the time of delivery.